



This test has been undertaken under the following conditions:

**Extrusion:** Cast Film.

**Sheet width:** 500 mm.

**Thickness:** 23 my.

**Composition:** 100% lineal low density Octene (LLDPE).

**Product:** 100 % Recyclable.

## DATA SHEET SuperProtex 220 automático

TECHNICAL PARAMETERS	ANALYSIS METHOD	UNIT OF MEASUREMENT	LONGITUDINAL STRENGTH	TRANSVERSE STRENGTH
Tacking	ASTM D-4649	105 gr.	-	-
Thickness	ISO-4593	23 micras	-	-
Punching shear resistance	Exxonmobil Method	30.2 N.	-	-
Density	ASTM D-1505	0.918 gr/cm <sup>3</sup> .	-	-
Flow rate	ASTM D-1238	2.8 g /10 min.	-	-
Elasticity	ASTM D-882	MPa.	9	8
Tearing	ASTM D-882	MPa.	42	28
Tearing deformation	ASTM D-882	%	500	830
Stretchable module	ASTM D-882	MPa.	140	150
Tear resistance (Elmendorf)	ASTM D-1922	Grs.	300	437
Impact resistance (Dart Test)	ASTM D-1709	Grs.	390	-
Guaranteed pre-stretching	PlastiFilm Lab	%	220	-
Maximum pre-stretching	PlastiFilm Lab	%	240	-